


RPE GEOMEMBRANE LINERS

PRODUCT DATA SHEETS

30 MIL REINFORCED POLYETHYLENE GEOMEMBRANE LINER



COATED FABRIC SPECIFICATIONS

Total Thickness 30±2 mils

Coating Type

Polyethylene

Total Weight (nominal) 18 oz/yd²

Sealing Properties

☐ Dielectric ☒ Thermal

MATERIAL PROPERTIES

	TEST METHOD	MINIMUM	TYPICAL
Tensile Strength, Grab (warp/fill)	ASTM D751A	250 / 250 lbs.	300 / 265 lbs.
Tensile Elongation, Grab (warp/fill)	ASTM D751A	25 / 25%	35 / 40%
Tear Strength, Tongue (warp/fill)	ASTM D5884	80 / 80 lbs.	161 / 188 lbs.
Puncture, Rod	ASTM D4833	75 lbs.	96 lbs.
Ply Adhesion Strength	ASTM D751	20 lbs. / in.	25 lbs. / in.
Low Temperature Bend	ASTM D2136	-70°F	-70°F
Abrasion Resistance (H18 / 1 kg)	ASTM D3389	5,000 cycles	6,000 cycles
Ozone Resistance (100 pphm @ 40°C)	ASTM D1149	Pass	Pass
Oxidative Induction Time	ASTM D3895	100 minutes	385 minutes
Hydraulic Conductivity	ASTM E96	1.0 x 10 ⁻¹² cm/sec	1.0 x 10 ⁻¹² cm/sec
Seam Shear Strength	ASTM D7747	90 lbs. / in.	97 lbs. / in.
Seam Peel Strength	ASTM D6636	20 lbs. / in.	36 lbs. / in.

Comments: This product is certified to AS4020 and NSF Std 61 for potable water containment.
This product meets the requirements of GRI GM-25 (Category 3 – Standard) specification.

The information provided by Ferguson is based on our manufacturer's research and is considered accurate, but we do not provide any warranty, expressed or implied, regarding the accuracy of this data or the results obtained from its use. The presented values are typical data and are not intended as limiting specifications. They represent the minimum expected measurements at the time of manufacture and are subject to revision as additional knowledge and experience are gained. Please contact Ferguson for additional information on warranties or values presented. We also do not guarantee that any use of this information will not infringe upon any patent. It is the sole responsibility of the user to determine the suitability and use of the information and materials provided for their specific application. Ferguson is not an installer of geosynthetic membranes, and the information is only provided as a guideline and not as an authority. Ferguson will not be held liable for the installation of geosynthetic membranes by others. Our standard terms and conditions of sale apply to all orders, and we exclude all liability for damages, including consequential damages exceeding the purchase price. No one is authorized to make oral warranties on our behalf, and we reserve the right to make changes without notice or obligation in our products and publications.

For more information about PVC Geomembrane Liners, contact Inside Sales at infogeo@ferguson.com or visit us at fergusonwaterworks.com

©2025 Ferguson Enterprises, LLC 0525

FERGUSON
WATERWORKS

36 MIL REINFORCED POLYETHYLENE GEOMEMBRANE LINER



COATED FABRIC SPECIFICATIONS

Total Thickness 36±3 mils

Coating Type

Polyethylene

Total Weight (nominal) 22 oz/yd²

Sealing Properties

☐ Dielectric ☒ Thermal

MATERIAL PROPERTIES

	TEST METHOD	MINIMUM	TYPICAL
Tensile Strength, Grab (warp/fill)	ASTM D751A	250 / 250 lbs.	300 / 280 lbs.
Tensile Elongation, Grab (warp/fill)	ASTM D751A	25 / 25%	45 / 35%
Tear Strength, Tongue (warp/fill)	ASTM D5884	80 / 80 lbs.	115 / 200 lbs.
Puncture, Rod	ASTM D4833	80 lbs.	95 lbs.
Ply Adhesion Strength	ASTM D751	20 lbs. / in.	30 lbs. / in.
Low Temperature Bend	ASTM D2136	-70°F	-70°F
Abrasion Resistance (H18 / 1 kg)	ASTM D3389	15,000 cycles	18,000 cycles
Ozone Resistance (100 pphm @ 40°C)	ASTM D1149	Pass	Pass
Oxidative Induction Time	ASTM D3895	100 minutes	600 minutes
Hydraulic Conductivity	ASTM E96	1.0 x 10 ⁻¹¹ cm/sec	1.0 x 10 ⁻¹¹ cm/sec
Seam Shear Strength	ASTM D7747	100 lbs. / in.	110 lbs. / in.
Seam Peel Strength	ASTM D6636	20 lbs. / in.	50 lbs. / in.

Comments: This product is certified to AS4020 and NSF Std 61 for potable water containment.
This product meets the requirements of GRI GM-25 (Category 2 – Moderate) specification.

The information provided by Ferguson is based on our manufacturer's research and is considered accurate, but we do not provide any warranty, expressed or implied, regarding the accuracy of this data or the results obtained from its use. The presented values are typical data and are not intended as limiting specifications. They represent the minimum expected measurements at the time of manufacture and are subject to revision as additional knowledge and experience are gained. Please contact Ferguson for additional information on warranties or values presented. We also do not guarantee that any use of this information will not infringe upon any patent. It is the sole responsibility of the user to determine the suitability and use of the information and materials provided for their specific application. Ferguson is not an installer of geosynthetic membranes, and the information is only provided as a guideline and not as an authority. Ferguson will not be held liable for the installation of geosynthetic membranes by others. Our standard terms and conditions of sale apply to all orders, and we exclude all liability for damages, including consequential damages exceeding the purchase price. No one is authorized to make oral warranties on our behalf, and we reserve the right to make changes without notice or obligation in our products and publications.

For more information about PVC Geomembrane Liners, contact Inside Sales at infogeo@ferguson.com or visit us at fergusonwaterworks.com

FERGUSON
WATERWORKS

©2025 Ferguson Enterprises, LLC 0525

45 MIL REINFORCED POLYETHYLENE GEOMEMBRANE LINER



COATED FABRIC SPECIFICATIONS

Total Thickness 45±4 mils

Coating Type

Polyethylene

Total Weight (nominal) 28 oz/yd²

Sealing Properties

☐ Dielectric ☐ Thermal

MATERIAL PROPERTIES

	TEST METHOD	MINIMUM	TYPICAL
Tensile Strength, Grab (warp/fill)	ASTM D751A	300 / 300 lbs.	400 / 355 lbs.
Tensile Elongation, Grab (warp/fill)	ASTM D751A	25 / 25%	35 / 35%
Tear Strength, Tongue (warp/fill)	ASTM D5884	80 / 80 lbs.	150 / 85 lbs.
Puncture, Rod	ASTM D4833	95 lbs.	105 lbs.
Ply Adhesion Strength	ASTM D751	20 lbs. / in.	30 lbs. / in.
Low Temperature Bend	ASTM D2136	-70°F	-70°F
Abrasion Resistance (H18 / 1 kg)	ASTM D3389	20,000 cycles	30,000 cycles
Ozone Resistance (100 pphm @ 40°C)	ASTM D1149	Pass	Pass
Oxidative Induction Time	ASTM D3895	100 minutes	600 minutes
Hydraulic Conductivity	ASTM E96	1.3 x 10 ⁻¹¹ cm/sec	1.3 x 10 ⁻¹¹ cm/sec
Seam Shear Strength	ASTM D7747	120 lbs. / in.	130 lbs. / in.
Seam Peel Strength	ASTM D6636	20 lbs. / in.	85 lbs. / in.

Comments: This product is certified to AS4020 and NSF Std 61 for potable water containment.
This product meets the requirements of GRI GM-25 (Category 1 – Severe) specification.

REVISION DATE: 16 Aug 2021 | EXPIRY DATE: 16 Aug 2026

The information provided by Ferguson is based on our manufacturer's research and is considered accurate, but we do not provide any warranty, expressed or implied, regarding the accuracy of this data or the results obtained from its use. The presented values are typical data and are not intended as limiting specifications. They represent the minimum expected measurements at the time of manufacture and are subject to revision as additional knowledge and experience are gained. Please contact Ferguson for additional information on warranties or values presented. We also do not guarantee that any use of this information will not infringe upon any patent. It is the sole responsibility of the user to determine the suitability and use of the information and materials provided for their specific application. Ferguson is not an installer of geosynthetic membranes, and the information is only provided as a guideline and not as an authority. Ferguson will not be held liable for the installation of geosynthetic membranes by others. Our standard terms and conditions of sale apply to all orders, and we exclude all liability for damages, including consequential damages exceeding the purchase price. No one is authorized to make oral warranties on our behalf, and we reserve the right to make changes without notice or obligation in our products and publications.

For more information about PVC Geomembrane Liners, contact Inside Sales at infogeo@ferguson.com or visit us at fergusonwaterworks.com

©2025 Ferguson Enterprises, LLC 0525

FERGUSON
WATERWORKS